

Magpol Kimya

magpol

DATASHEET

MAXOPOL TD 6000

POLYPROPYLENE GLYCOL TRIOL FOR PU FOAM AND CASE

CHEMICAL COMPOSITION

At room temperature viscous liquid

APPLICATIONS

Maxopol TD 6000 is 6000 molecular weight triol, widely used for CASE applications and cold-molded products and also for high resilience polyurethane foams.

TYPICAL PROPERTIES

PROPERTY	UNIT	VALUE
Appearance	-	colorless liquid
Hydroxyl Value	mg KOH/g	26-29
Color	APHA	Max 30
Viscosity at 25 C	mPa.s	1060-1200
Moisture	% wt	Max 0.06
Acidity	mg KOH/g	Max 0.05
pH	-	8.0-9.5

STORAGE STABILITY

15 C - 30 C in closed drum IBC or Container for 12 months

SAFETY And HANDLING

Please refer to our Material Safety Data sheets

PACKAGING

Tight head Drum, IBC or Bulk Container

DISCLAIMER

The information and data contained in this publication is the best of our knowledge, true and accurate but any recommendations or suggestions which may be made are without guarantee since the conditions of use are beyond our control.

The product properties may be changed without any notice.

No liability, warranty or guarantee of product performance is created by this document.

It is the Buyer's responsibility to determine whether products are appropriate for Buyer's use and to ensure that Buyer's workplace and disposal practices are in compliance with applicable laws and regulations.

Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing patents covering any material or its use.

MAGPOL KİMYA SANAYİ ve TİCARET A.Ş

Yenişehir Mahallesi Osmanlı Bulvarı, Arwen İş Merkezi

B Blok No:5 D 10 34912 - Pendik - İSTANBUL - TURKEY

Tel : + 90 216 592 3992 Fax : +90 216 592 1774

www.magpolkimya.com

info@magpolkimya.com